

DENSYL MASTIC BLANKETS

Pre-Formed Molding Mastic

Description

Densyl Mastic Blankets are preformed sheets of mastic supported by a fabric backing. It is a petrolatum compound containing inert siliceous fillers and vegetable fibers. The preformed mastic is backed with a synthetic fiber fabric fully impregnated with a petrolatum compound.

Uses

Densyl Mastic Blankets are used to contour flanges, couplings, valves and irregular surfaces. It is applied prior to the tape application and generally used in conjunction with primer, Denso Petrolatum Tapes or Denso Bituminous Tapes.

Features

- Excellent sealing properties
- No VOCs
- Will adhere to metal, PVC, polyethylene and concrete
- Not effected by water, acids and salts
- Easy application
- Inert and environmentally stable
- Minimal surface preparation (SSPC SP 2-3)
- Meets AWWA C217 Standard.
- CSA Z245.30 component

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi is also suitable. Apply a thin film of appropriate primer to the surface. Then, by hand application, mold the mastic blanket to a rounded configuration to fill irregular shapes and reduce sharp edged surfaces.



Densyl Mastic Blankets

Property Specifications

PROPERTIES

Specific Gravity	1.39
Specific Volume	20 in ³ /lb
Flash Point	>356°F
Maximum Service Temperature	194°F
Thickness	3/8" to 1/2"

Quantity Estimates

Pipe Diameter	Flanged Joint	Flanged Valve	Dresser Coupling
in.	ea.	ea.	ea.
10	2	6	2
12	2.5	7.5	2.5
14	2.5	17.5	2.5
16	3	9	3
18	3.5	10.5	3
20	4	12	4
24	4.5	13.5	4
30	5	15	6
36	6	18	6
54	12	36	12

PACKAGING:

BLANKETS

5 each 10" x 39" = 44 lbs per case



Unconventional Solutions, Inc. - Partnering with Your Industry to Repair - Protect - Upgrade

MI HQ 28056 Oakland Oaks Ct., Wixom, MI 48393 | 248.735.7000 | www.USIgroups.com

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.