# PRODUCT DATA SHEET

	DENSO PASTE Petrolatum Tape Primer
Description	Denso Paste is a soft brown petrolatum primer containing moisture displacing corrosion inhibiting compounds for application by stiff brush or gloved hand at normal ambient temperature. It does not dry, harden or crack.
Uses	Primarily used as a primer prior to the application of Denso petrolatum tapes. Denso Paste will penetrate existing rust, displace moisture, pacify the surface and aid the adhesion of petrolatum tapes and mastics. It is also used as a temporary coating for exposed metal.
Features	<ul> <li>Minimal surface preparation (SSPC SP 2-3)</li> <li>Can be applied in any climate</li> <li>Can be applied to wet surfaces</li> <li>Contains no V.O.C.'s</li> <li>Can be applied by inexperienced personnel</li> <li>No shut downs necessary</li> <li>Meets AWWA C-217</li> <li>CSA Z245.30 compliant</li> </ul>
Application	Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3.000 - 7.000 psi is also suitable. Apply a thin uniform coat of Denso Paste to entire

SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water was of 3,000 - 7,000 psi is also suitable. Apply a thin uniform coat of Denso Paste to entire surface with gloved hand, brush or rag.



USI - MI HQ 248.735.7000 • www.USIgroups.com

# **Denso Paste**

## **PROPERTY SPECIFICATIONS**

### **Properties**

Solids Content	>98%	
Specific Gravity	1.08	
Specific Volume	26 cu in/lb.	
Flash Point	>356°F	
Maximum Service Temperature	158°F	
Coverage (Per Pail)	22 ft²/lb.	
Packaging	4 ea 5.5 lb tubs	

### **COVERAGE PER CASE:**

484 ft<sup>2</sup> per case

#### PACKAGING:

4 each 5.5 lb tubs per case

Also available in 55 lb pails



USI Unconventional Solutions, Inc. - Partnering with Your Industry to Repair - Protect - Upgrade

MI HQ 28056 Oakland Oaks Ct., Wixom, MI 48393 | 248.735.7000 | www.USIgroups.com

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.