



RESIMETAL 204 Heavy Duty Ceramic Repair Paste –

Solvent free epoxy with ceramic beads for medium sliding abrasion

Resimetal 204 Heavy Duty Ceramic Repair Paste is a two component solvent free epoxy repair compound which contains 0.2mm – 1.5mm ceramic beads. The product is ideal for resurfacing and protecting metallic substrates subject to medium sliding abrasion.

- Apply to abrasive blast cleaned surfaces
- High mechanical adhesion to metal substrates
- Ideal for fluids with high solids content

Typical Applications

Pipe bends	Chutes Pipe	Hoppers	Valves
Pumps	surfaces		

Surface Preparation

Metallic Substrates – Abrasive blast cleaning

- 1. All oil and grease must be removed from the surface using an appropriate cleaner such as MEK.
- 2. All surfaces must be abrasive blasted to *ISO 8501/4 Standard SA2.5 (SSPC SP10/ NACE 2)* minimum blast profile of 75 microns (3mil) using an angular abrasive.
- 3. Once blast cleaned, the surface must be degreased and cleaned using MEK or similar type material.
- 4. All surfaces must be coated before gingering or oxidation occurs.

PLEASE NOTE: For salt contaminated surfaces the substrate must be pressure washed with clean water and checked for salt contamination, please refer to the surface preparation and pre-application guide for further information.

Mixing

Prior to mixing please ensure the following:

- 1. The base component is at a temperature between 60-77F°.
- 2. The ambient & surface temperature is above 50F°.
- 3. The ambient & surface temperatures are not less than 6°F above the dew point.
- Once these 3 checks have been met, please proceed with mixing the product.
 - 1. Mixing of the product can be on full units or by part-mixing.
 - 2. If mixing the whole unit please ensure as much of the base and activator is dispensed from the plastic container onto a clean plastic mixing surface.
 - 3. Mix using the spatula provided until a uniform material free of any streakiness is achieved while ensuring no unmixed material is left on the spatula or the mixing surface.
 - 4. From the commencement of mixing the whole of the material should be used within 50 minutes at 68F°.
 - 5. For part mixing, using a spatula place 3 equal measures from the base unit onto a clean plastic mixing surface. Clean the spatula thoroughly and then take 1 equal measure from the Activator unit and place alongside the base measures. Mix as above.

Application

- 1. Using the spatula or applicator tool, apply the material to the blast prepared surface,
- 2. Ensure the product is pressed into any holes, scars or cracks and profile the repair to a smooth finish.
- 3. Apply in a single coat at wet film thickness of 80-160mils.

Coverage Rates

5kg (11lb) of fully mixed product will give the following coverage rates -

15.70ft² at 80mil

7.848ft² at 160mil

Please note that the coverage rates quoted are theoretical and do not take into consideration the profile or condition of the surface being repaired.





Cure Times

At 68F° the applied materials should be allowed to harden for the times indicated below before being subjected to the conditions indicated. These times will be extended at lower temperatures and reduced at higher temperatures: Usable Life 50mins

4 hours

8 hours

4 days

Usable Life Minimum overcoating time Maximum overcoating time Full cure

For Optimum Performance

After an initial curing period of at least 4 hours at 68F°, raising the cure temperature progressively to 140-212F° for up to 8 hours will result in improved mechanical, thermal and chemical resistance properties

Pack Sizes

This product is available in the following pack sizes – 1.5kg (3.3lb), 5kg (11lb)

Color

Mixed material – Mid grey or red Base component – Mid grey or red Activator component – dark grey

Over-coating times

Minimum - the applied material can be over-coated as soon as it is touch dry. Maximum - the over-coating time should not exceed 8 hours at 68F°. Where the maximum over-coating time is exceeded, the material should be allowed to harden before being abraded or flash blasted to remove surface contamination.

Storage Life

5 years if unopened and store in normal dry conditions (60-86°F)

Other Technical Documents

Quick Application Guide	-	Hand application
Safety Data Sheets	-	Base & Activator components
Product Specification Sheet	-	Technical Performance Information

Health and Safety

Please ensure good practice is observed at all times. Protective gloves, goggles & a disposable coverall must be worn during the mixing and application of this product. Before mixing and applying the material ensure you have read the fully

detailed Safety Data Sheet.

Legal Notice:

The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine if the product is suitable for use. Resimac accepts no liability arising out of the use of this information or the product described herein.

